

(19)



JAPANESE PATENT OFFICE

PATENT ABSTRACTS OF JAPAN

(11) Publication number: **2000128648 A**

(43) Date of publication of application: **09.05.00**

(51) Int. Cl.

C04B 35/64
B28B 3/00

(21) Application number: **10302888**

(22) Date of filing: **23.10.98**

(71) Applicant: **ASAHI OPTICAL CO LTD**

(72) Inventor: **MIYAKE SHOTARO**
KUBOTA YUKIO
HIRAIDE TSUNEO

(54) **PRODUCTION OF SINTERED BODY**

(57) Abstract:

PROBLEM TO BE SOLVED: To provide a method for producing a sintered body, enabling the production of the homogeneous sintered article hardly having sintering defects on the discharge plasma sintering.

SOLUTION: This method for producing a sintered body comprises preparing a powder material such as ceramic powder as a raw material, isotropically adding a pressure to the powder material by a method such as a hydrostatic pressurization method (CIP, HIP) to pressure-compact the powder material, applying a mechanical processing such as a cutting processing, a grinding processing or a polishing processing to the pressurized powder article to arrange the shape or dimension, and subsequently sintering the processed powder article by a discharge plasma sintering method to obtain the sintered body. The discharge plasma sintering is carried out by filling the pressurized powder in a molding die, pressurizing the filled powder with a pair of molding punches and simultaneously applying electric pulses to the filled material.

Therein, it is preferable that a heat-insulating material is placed between the pressurized powder material and both the molding punches.

COPYRIGHT: (C)2000,JPO

